

DEFINITION

PROTAVIC® PNE 30252 is a dam resin with high viscosity and thixotropy designed for chip encapsulation.

PRODUCT DESCRIPTION

Appearance	Paste	
Odour	Slight	
Colour	Black	
Guaranteed specification	Standard	Method
Viscosity CP51 at 25°C and 2 rpm	105 000 ± 15 000 mPa.s	NFT 51211
Other informations	Typical Values	Methods
Thixotropic Index (0.2 / 2 rpm)	3.7	NFT 51211
Density	1.76 approx.	NFT 51201
Filler particle size	< 100 µm	ISO 1524
Filler content	72 % typical	TGA 1
Work life at 20°C (+25% viscosity increase)	1 day	NFT 51211
Pot life at 20°C (+100% viscosity increase)	> 2 days	NFT 51211

APPLICATION PROPERTIES

The rheological behaviour of **PROTAVIC® PNE 30252** is suited for dam application. It is strongly recommended to use **PROTAVIC® PNE 30252** (dam) with **PROTAVIC® PNE 30270** (fill). Both products are very similar in composition, thus they are chemically compatible and can be co-cured after chip encapsulation.

After curing, **PROTAVIC® PNE 30252** exhibits good adhesion on many substrates such as glass fiber epoxy.

After curing, **PROTAVIC® PNE 30252** provides good environmental and mechanical protection to chip.

USING PROTAVIC® PNE 30252

1 - Application process and rheological properties

PROTAVIC® PNE 30252 should be protected from moisture before use.

PROTAVIC® PNE 30252 can be applied with a micro-dispenser.

The rheological behaviour of **PROTAVIC® PNE 30252** provides a geometrically stable dam after dispensing and during curing cycle.

2 - Cure schedule

PROTAVIC[®] PNE 30252 cures at moderate temperature. Typical curing cycle is 20 minutes at 150°C.

TYPICAL PROPERTIES OF CURED PROTAVIC[®] PNE 30252

Properties	Typical Values	Methods
Shore D hardness	90 approx.	NFT 51109
Glass transition temperature	140 °C approx.	TMA 1
Coefficient of thermal expansion from 40 to 120°C	$24 \times 10^{-6} / ^\circ\text{C}$	TMA 1
Decomposition temperature	> 400 °C	TGA 1
Water absorption by water immersion 24h at RT	0.1 %	R 10-05

STORAGE CONDITIONS

PROTAVIC[®] PNE 30252 must be stored in original sealed container protected from moisture at temperature below -20°C to get a maximum period of storage (3 months).

Usual packaging: syringes, other packaging on demand.

PRECAUTIONS OF USE

Refer to enclosed safety data sheet.

DISCLAIMER

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Protavic International specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Protavic International's products. Protavic International specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Protavic International patents that may cover such processes or compositions. We recommend that each prospective user tests his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more European or foreign patents or patent applications.